

# Rust Converter/Sealer 14540, 14542, 14544

This high-tech formula halts residual rust in its tracks and converts it into a black protective polymeric coating that eliminates the need for sanding. The converted protective coating is a suitable primer, compatible with most top coats. Additionally, the protective coating will seal the surface against moisture to prevent future rust growth. Simply remove loose rust with a wire brush, then apply Pro Form Rust Converter/Sealer. Allow to dry, then top coat it with a quality coating. Single component; no more mixing. May be left exposed or topcoated.

PRODUCT	COLOR	SIZE
14540	Black (Off white color before use)	U.S. Pint (473 ml)
14542	Black (Off white color before use)	U.S. Quart (946 ml)
14546	Black (Off white color before use)	U.S. Gallon (3.78 L)

# READ ALL INSTRUCTIONS AND SAFETY PROCEDURES PRIOR TO USING!

IMPORTANT! This product contains hazardous materials.

Proper protective equipment should be used at all times. Please consult labels on each product as well as the safety data sheet for complete safe handling procedures and personal protection information.

NOTE: TEST ON A HIDDEN AREA BEFORE USING TO MAKE SURE THE PRODUCT PERFORMS TO YOUR SATISFACTION.

## SUITABLE SUBSTRATES:

Metal

### ADVANTAGES:

- Prevent future rust growth
- Converts rust into black protective polyremic coating
- Does not require sanding

#### PREPARATION:

Degrease and remove loose scale and paint with a wire brush. Rinse with water to remove salt or chemicals and allow to dry. It is not necessary to remove all traces of rust.

### MIXING:

Shake or stir thoroughly. The use of rubber gloves is recommended to avoid staining hands. Pour Rust Converter/Sealer into a plastic or glass container.



# **Rust Converter/Sealer** 14540, 14542, 14544

#### TECHNICAL DATA:

	14540, 14542, 14544	
Physical State	Liquid	
Color:	No data	
Odour:	Mild, Fruity odour	
Solubility:	Miscible	
Flash point:	71°C / 159.8°F (estimate; lowest flash point ingredient)	
Auto ignition temperature:	Not available	
VOC	0.52 lb/usg - 62.31 g/L	

#### PRECAUTIONARY INFORMATION

Refer to product label and Safety Data Sheet for health and safety information before using this product.

#### SAFETY CONSIDERATION

Safety Data Sheets are available at www.proformproducts.com or upon request at info@proformproducts.com. These are provided to help our customers satisfy their own handling, safety and disposal needs, and those required by local applicable health and safety regulations. Our Safety data sheets are updated regularly, therefore, please review the most current Safety Data Sheet before handling or using any product.

#### TECHNICAL INFORMATION

The technical information, recommendations and other statements contained in this document are based upon tests or experience that Pro Form believes are reliable, but the accuracy or completeness of such information is not guaranteed.

#### PRODUCT USE

August 2020

Many factors beyond Pro Form's control and uniquely within user's knowledge and control can affect the use and performance of a Pro Form product in a particular application. Given the variety of factors that can affect the use and performance of a Pro Form product, user is solely responsible for evaluating the Pro Form product and determining whether it is fit for a particular purpose and suitable for user's method of application.

#### WARRANTY, LIMITED REMEDY, DISCLAIMER AND LIMITATION OF LIABILITY

Pro Form Products Ltd. ("Pro Form") makes no warranty, either express or implied, and specifically excludes any implied warranties or conditions of quality, whether of merchantability, fitness or otherwise. On any claim, irrespective of the legal theory invoked, Pro Form's total liability shall not exceed the purchase price of the product. At its option, Pro Form may instead replace or repair the product. In no event shall Pro Form be liable for any damages of any type, or for loss. The technical information, recommendations and other statements contained in this document are based upon tests or experience that Pro Form believes are reliable, but the accuracy or completeness of such information is not guaranteed.