

Revolution Flowable Blending & Finishing Putty PF 128, PF 121, PF 122

A flowable polyester glazing putty designed to fill pinholes, sanding scratches and minor imperfections. It can be spread over a much larger area than conventional glazing putties, and allows imperfections to be filled without altering contour. Can be spread extremely thin and sanded to an ultra-fine featheredge. Use over sanded substrates, steel and galvanized steel. When mixed within body fillers, it improves spreading and sanding. Cream hardener included.

PRODUCT	SIZE	HARDENER
PF 128	150 ml (5 fl oz)	PF 138 14 g (0.5 oz)
PF 121	710 ml (24 fl oz)	PF 140 28 g (1 oz)
PF 122	30 fl oz (880 ml)	PF 140 28 g (1 oz)

READ ALL INSTRUCTIONS AND SAFETY PROCEDURES PRIOR TO USING!

IMPORTANT! This product contains hazardous materials.

Proper protective equipment should be used at all times. Please consult labels on each product as well as the safety data sheet for complete safe handling procedures and personal protection information.

NOTE: TEST ON A HIDDEN AREA BEFORE USING TO MAKE SURE THE PRODUCT PERFORMS TO YOUR SATISFACTION.

SUITABLE SUBSTRATES

- Steel
- Galvanized metal
- Aluminum

ADVANTAGES

- Spreads easily
- Easy sanding
- Excellent skim coat
- Stain free

SURFACE PREPARATION:

1. Surface must be free of rust, wax, silicone, grease, dirt and other contaminants.
2. Clean metal surfaces with PF 605 Wax and Grease Remover (Strong). Wipe dry while the surface is still wet.
3. Sand substrate with 180-240 grit abrasive.
4. Use clean dry air and blow surface free of dirt.

MIXING DIRECTIONS:

Mixing Ratio: 2% by weight. Mix 2% of cream hardener to PF 128, PF 121, PF 122. Knead cream hardener tube before using. Using a non contaminated mixing board, mix thoroughly until mixture is color consistent.

DIRECTIONS FOR USE:

1. Mix the desired quantity of product.
2. Apply filler with a clean spreader. Fill should not exceed 1.5 mm (1/16") in depth. Heavier applications may sag on vertical surfaces.
3. Allow to cure thoroughly.
4. Sand with 120-180 grit until desired contour is achieved.

5. Topcoat with a premium quality primer.

Caution: Do not return catalyzed material to can. Avoid contamination, keep cap closed after use.

TECHNICAL DATA:

	PF 128, PF 121, PF 122
Physical State	Paste
Color:	Light Yellow
Odour:	Hydrocarbon odour
Solubility :	Slightly soluble in water
Flash point:	32°C (89.6°F) (Closed Cup)
Auto ignition temperature:	490°C (914°F)
VOC	42 g/L • 0.35 lbs/US gal

PRECAUTIONARY INFORMATION

Refer to product label and Safety Data Sheet for health and safety information before using this product.

SAFETY CONSIDERATION

Safety Data Sheets are available at www.proformproducts.com or upon request at info@proformproducts.com. These are provided to help our customers satisfy their own handling, safety and disposal needs, and those required by local applicable health and safety regulations. Our Safety data sheets are updated regularly, therefore, please review the most current Safety Data Sheet before handling or using any product.

TECHNICAL INFORMATION

The technical information, recommendations and other statements contained in this document are based upon tests or experience that Pro Form believes are reliable, but the accuracy or completeness of such information is not guaranteed.

PRODUCT USE

Many factors beyond Pro Form's control and uniquely within user's knowledge and control can affect the use and performance of a Pro Form product in a particular application. Given the variety of factors that can affect the use and performance of a Pro Form product, user is solely responsible for evaluating the Pro Form product and determining whether it is fit for a particular purpose and suitable for user's method of application.

WARRANTY, LIMITED REMEDY, DISCLAIMER AND LIMITATION OF LIABILITY

Pro Form Products Ltd. ("Pro Form") makes no warranty, either express or implied, and specifically excludes any implied warranties or conditions of quality, whether of merchantability, fitness or otherwise. On any claim, irrespective of the legal theory invoked, Pro Form's total liability shall not exceed the purchase price of the product. At its option, Pro Form may instead replace or repair the product. In no event shall Pro Form be liable for any damages of any type, or for loss. The technical information, recommendations and other statements contained in this document are based upon tests or experience that Pro Form believes are reliable, but the accuracy or completeness of such information is not guaranteed.