

Metal Filler Aluminum Reinforced Filler PF 160

A metal-reinforced compound ideal for your finest metalwork, leveling and filling rust repairs, spot welds and rivets. Excellent rustproofing, moisture and fuel resistance characteristics. Liquid hardener included.

PRODUCT

SIZE

HARDENER

PF 160

750 ml (25.3 fl oz)

PF 145 14 ml (0.5 fl oz)

READ ALL INSTRUCTIONS AND SAFETY PROCEDURES PRIOR TO USING!

IMPORTANT! This product contains hazardous materials.

Proper protective equipment should be used at all times. Please consult labels on each product as well as the safety data sheet for complete safe handling procedures and personal protection information.

NOTE: TEST ON A HIDDEN AREA BEFORE USING TO MAKE SURE THE PRODUCT PERFORMS TO YOUR SATISFACTION.

SUITABLE SUBSTRATES

- Aluminum

ADVANTAGES

- High strength
- Waterproof
- Multi purpose
- Easy to spread

SURFACE PREPARATION:

1. Surface must be free of rust, wax, silicone, grease, dirt and other contaminants.
2. Wash surface with soap and water.
3. Clean metal surfaces with PF 605 Wax and Grease Remover (Strong), fibreglass surfaces with PF 606 Plastic Parts Cleaner. Wipe dry while the surface is still wet.
4. Grind metal surfaces using 36 grit disc, fibreglass with 180 grit.
5. Use clean dry air and blow surface free of dirt.
6. For maximum adhesion, apply directly to bare metal.

MIXING DIRECTIONS:

Mixing Ratio: 2%. Mix 2% of liquid hardener to PF 160. Approximately 15 drops to a golf ball size of filler. Using a non contaminated mixing board, mix thoroughly until mixture is consistent.

DIRECTIONS FOR USE:

1. Mix the desired quantity of product.
2. Apply PF 160 firmly using a clean spreader to fill area and insure maximum adhesion. Press product between welds for a waterproof repair.
3. Allow to cure thoroughly.
4. Break with 80, and follow with 120 grit abrasive to achieve desired contour. Final finish with finer abrasive.
5. If required, skimcoat with PF 121 Revolution Flowable Blending and Finishing Putty.
6. Topcoat with a premium quality primer.

Caution: Do not return catalyzed material to can. To avoid contamination, keep cap closed after use.

TECHNICAL DATA:

	PF 160
Physical State	Paste
Color:	No data
Odour:	Hydrocarbon odour
Solubility :	Slightly soluble in water
Flash point:	31°C (87.8°F) (estimated)
Auto ignition temperature:	490°C (914°F)
VOC	55.12 g/L • 0.46 lbs/gal

PRECAUTIONARY INFORMATION

Refer to product label and Safety Data Sheet for health and safety information before using this product.

SAFETY CONSIDERATION

Safety Data Sheets are available at www.proformproducts.com or upon request at info@proformproducts.com. These are provided to help our customers satisfy their own handling, safety and disposal needs, and those required by local applicable health and safety regulations. Our Safety data sheets are updated regularly, therefore, please review the most current Safety Data Sheet before handling or using any product.

TECHNICAL INFORMATION

The technical information, recommendations and other statements contained in this document are based upon tests or experience that Pro Form believes are reliable, but the accuracy or completeness of such information is not guaranteed.

PRODUCT USE

Many factors beyond Pro Form’s control and uniquely within user’s knowledge and control can affect the use and performance of a Pro Form product in a particular application. Given the variety of factors that can affect the use and performance of a Pro Form product, user is solely responsible for evaluating the Pro Form product and determining whether it is fit for a particular purpose and suitable for user’s method of application.

WARRANTY, LIMITED REMEDY, DISCLAIMER AND LIMITATION OF LIABILITY

Pro Form Products Ltd. (“Pro Form”) makes no warranty, either express or implied, and specifically excludes any implied warranties or conditions of quality, whether of merchantability, fitness or otherwise. On any claim, irrespective of the legal theory invoked, Pro Form’s total liability shall not exceed the purchase price of the product. At its option, Pro Form may instead replace or repair the product. In no event shall Pro Form be liable for any damages of any type, or for loss. The technical information, recommendations and other statements contained in this document are based upon tests or experience that Pro Form believes are reliable, but the accuracy or completeness of such information is not guaranteed.