

A one-step solvent-based, fast-drying formulation to be used in the final surface preparation when bonding urethane adhesives to glass, primed metals and pinchweld. This low conductive primer blocks 100% of harmful UV rays and maximizes adhesion between the glass and the pinchweld.

PRODUCT	SIZE
---------	------

PF 230	30 ml (1.07 fl oz)
--------	--------------------

READ ALL INSTRUCTIONS AND SAFETY PROCEDURES PRIOR TO USING!

IMPORTANT! This product contains hazardous materials.

Proper protective equipment should be used at all times. Please consult labels on each product as well as the safety data sheet for complete safe handling procedures and personal protection information.

NOTE: TEST ON A HIDDEN AREA BEFORE USING TO MAKE SURE THE PRODUCT PERFORMS TO YOUR SATISFACTION.

FEATURES

- Improves adhesion of Fast Cure Urethane Windshield Adhesive to pinchweld and glass.

DIRECTIONS FOR USE:

Clean the glass (both sides) with PF 513 Glass Cleaner. Let dry thoroughly. Using PF 644 dauber, apply a thin film to a pre-cleaned glass bond line surface, bare metal and pinch weld. Allow to dry at least 10 minutes (above -2°C / 30°F) or 20 minutes if below. Apply urethane adhesive as per its instructions.

Newly painted surfaces must be thoroughly dry and scuffed before applying the primer.

NOTE: PF 230 HAS A LIMITED SHELF LIFE (12 MONTHS). DO NOT OVERSTOCK.

WARNING: FLAMMABLE LIQUID AND VAPOR. SKIN AND EYE IRRITANT.

TECHNICAL DATA:

	PF 230
Physical State	Liquid
Appearance:	Black
Odour:	Solvent odour
Solubility :	Not available
Flash point:	-10°C (14°F)
Auto ignition temperature:	400°C (752°F)
VOC	(Directive 2010/75/EC) 588.1 g/L • 4.91 lbs/usc (volatile carbon) 410.98 g/L • 3.43 lbs/usc

PRECAUTIONARY INFORMATION

Refer to product label and Safety Data Sheet for health and safety information before using this product.

SAFETY CONSIDERATION

Safety Data Sheets are available at www.proformproducts.com or upon request at info@proformproducts.com. These are provided to help our customers satisfy their own handling, safety and disposal needs, and those required by local

applicable health and safety regulations. Our Safety data sheets are updated regularly, therefore, please review the most current Safety Data Sheet before handling or using any product.

TECHNICAL INFORMATION

The technical information, recommendations and other statements contained in this document are based upon tests or experience that Pro Form believes are reliable, but the accuracy or completeness of such information is not guaranteed.

PRODUCT USE

Many factors beyond Pro Form's control and uniquely within user's knowledge and control can affect the use and performance of a Pro Form product in a particular application. Given the variety of factors that can affect the use and performance of a Pro Form product, user is solely responsible for evaluating the Pro Form product and determining whether it is fit for a particular purpose and suitable for user's method of application.

WARRANTY, LIMITED REMEDY, DISCLAIMER AND LIMITATION OF LIABILITY

Pro Form Products Ltd. ("Pro Form") makes no warranty, either express or implied, and specifically excludes any implied warranties or conditions of quality, whether of merchantability, fitness or otherwise. On any claim, irrespective of the legal theory invoked, Pro Form's total liability shall not exceed the purchase price of the product. At its option, Pro Form may instead replace or repair the product. In no event shall Pro Form be liable for any damages of any type, or for loss. The technical information, recommendations and other statements contained in this document are based upon tests or experience that Pro Form believes are reliable, but the accuracy or completeness of such information is not guaranteed.