

Pro Guard Rubberized Gravlguard PF 532

A tough textured rubberized gravlguard coating for protecting rocker panels from stone chips and other road abrasions. It is paintable and flexible. Excellent adhesion to painted or bare metals.

PRODUCT	SIZE	COLOR
PF 532	560 g (19.75 oz)	Black

READ ALL INSTRUCTIONS AND SAFETY PROCEDURES PRIOR TO USING!

IMPORTANT! This product contains hazardous materials.

Proper protective equipment should be used at all times. Please consult labels on each product as well as the safety data sheet for complete safe handling procedures and personal protection information.

NOTE: TEST ON A HIDDEN AREA BEFORE USING TO MAKE SURE THE PRODUCT PERFORMS TO YOUR SATISFACTION.

SUITABLE SUBSTRATES:

- Metals
- Plastics

ADVANTAGES:

- Paintable
- Fast drying
- Rustproofs
- Accepts most automotive paints
- More textured than PF 560

DIRECTIONS FOR USE:

- 1. Shake can for 1 minute after mixing ball moves freely. NOTE: Insufficient mixing may cause permanent plugging of the spray head.
- 2. Surface must be free of rust, wax, silicone, grease, dirt and other contaminants.
- 3. For optimal protection, bare metal should be primed. Use PF 654, Aerosol Self Etching Primer, or Epoxy Primer PF 660C and PF 661C.
- 4. Spray can approximately 25 to 30 cm (10 to 12 inches) from surface. Distance will determine texture.
- 5. To assure that entire contents will be dispensed, always have the dot on the can rim facing towards surface to be sprayed.
- 6. Can be painted in 1 hour under normal shop conditions. Low temperatures 16°C (60°F) or high humid conditions 21°C (70°F) or more allow 30 minutes more of dry time.
- 7. When finished, turn can upside down and spray about 3 seconds to clean out spray head. Save spray heads in a small can of paint thinner as spares.

TECHNICAL DATA:

	PF 532
Physical State:	Aerosol
Color:	Black
Odour:	Solvent odour



Pro Guard Rubberized Gravlguard PF 532

Solubility:	No data	
Flash point:	-4.0°C (24.8°F)	
Auto ignition temperature:	> 232°C (> 450°F)	
VOC:	2.49 lbs/usg • 328.3 g/L	

PRECAUTIONARY INFORMATION

Refer to product label and Safety Data Sheet for health and safety information before using this product.

SAFETY CONSIDERATION

Safety Data Sheets are available at www.proformproducts.com or upon request at info@proformproducts.com. These are provided to help our customers satisfy their own handling, safety and disposal needs, and those required by local applicable health and safety regulations. Our Safety data sheets are updated regularly, therefore, please review the most current Safety Data Sheet before handling or using any product.

TECHNICAL INFORMATION

The technical information, recommendations and other statements contained in this document are based upon tests or experience that Pro Form believes are reliable, but the accuracy or completeness of such information is not guaranteed.

PRODUCT USE

Many factors beyond Pro Form's control and uniquely within user's knowledge and control can affect the use and performance of a Pro Form product in a particular application. Given the variety of factors that can affect the use and performance of a Pro Form product, user is solely responsible for evaluating the Pro Form product and determining whether it is fit for a particular purpose and suitable for user's method of application.

WARRANTY, LIMITED REMEDY, DISCLAIMER AND LIMITATION OF LIABILITY

Pro Form Products Ltd. ("Pro Form") makes no warranty, either express or implied, and specifically excludes any implied warranties or conditions of quality, whether of merchantability, fitness or otherwise. On any claim, irrespective of the legal theory invoked, Pro Form's total liability shall not exceed the purchase price of the product. At its option, Pro Form may instead replace or repair the product. In no event shall Pro Form be liable for any damages of any type, or for loss. The technical information, recommendations and other statements contained in this document are based upon tests or experience that Pro Form believes are reliable, but the accuracy or completeness of such information is not guaranteed.