

**European Texture
Rubberized Gravlguard
PF 560, PF 565, PF 566**

A tough textured coating for protecting rocker panels and valence panels from stone chips and other road abrasions. Excellent adhesion to painted or primed metals.

PRODUCT	SIZE	COLOR
PF 560	446 g (15.75 oz)	Black
PF 565	446 g (15.75 oz)	Off White
PF 566	446 g (15.75 oz)	Grey

**READ ALL INSTRUCTIONS AND SAFETY PROCEDURES PRIOR TO USING!
IMPORTANT! This product contains hazardous materials.**

Proper protective equipment should be used at all times. Please consult labels on each product as well as the safety data sheet for complete safe handling procedures and personal protection information.

NOTE: TEST ON A HIDDEN AREA BEFORE USING TO MAKE SURE THE PRODUCT PERFORMS TO YOUR SATISFACTION.

SUITABLE SUBSTRATES:

- Metals
- Plastics

ADVANTAGES:

- Paintable
- Fast drying
- Rustproofs
- Accepts most automotive paints

DIRECTIONS FOR USE:

1. Shake can for 1 minute after mixing ball moves freely. NOTE: Insufficient mixing may cause permanent plugging of the sprayhead.
2. Surface must be free of rust, wax, silicone, grease, dirt and other contaminants.
3. Bare metal should be primed. Use PF 654, Aerosol Self Etching Primer, or Epoxy Primer PF 660C and PF 661C.
4. Spray can approximately 25 to 30 cm (10 to 12 inches) from surface. Distance will determine texture.
5. To assure that entire contents will be dispensed, always have the dot on the can rim facing towards surface to be sprayed.
6. Can be painted in 1 hour under normal shop conditions. Low temperatures 16°C (60°F) or high humid conditions 21°C (70°F) or more allow 30 minutes more of dry time.
7. When finished, turn can upside down and spray about 3 seconds to clean out sprayhead. Save sprayheads in a small can of paint thinner as spares.

TECHNICAL DATA:

	PF 560	PF 565	PF 566
Physical State:	Aerosol		
Color:	Black	Off White	Grey
Odour:	Solvent odour	Solvent odour	Solvent odour

Solubility :	No data	Slightly soluble in water	Slightly soluble in water
Flash point:	-4.0°C (24.8°F)	4°C (39.2°F)	4°C (39.2°F)
Auto ignition temperature:	> 232°C (> 450°F)	232°C (450°F)	No Data
VOC:	2.49 lbs/usg • 328.3 g/L	2.53 lbs/usg • 303.17 g/L	2.54 lbs/usg • 305 g/L

PRECAUTIONARY INFORMATION

Refer to product label and Safety Data Sheet for health and safety information before using this product.

SAFETY CONSIDERATION

Safety Data Sheets are available at www.proformproducts.com or upon request at info@proformproducts.com. These are provided to help our customers satisfy their own handling, safety and disposal needs, and those required by local applicable health and safety regulations. Our Safety data sheets are updated regularly, therefore, please review the most current Safety Data Sheet before handling or using any product.

TECHNICAL INFORMATION

The technical information, recommendations and other statements contained in this document are based upon tests or experience that Pro Form believes are reliable, but the accuracy or completeness of such information is not guaranteed.

PRODUCT USE

Many factors beyond Pro Form’s control and uniquely within user’s knowledge and control can affect the use and performance of a Pro Form product in a particular application. Given the variety of factors that can affect the use and performance of a Pro Form product, user is solely responsible for evaluating the Pro Form product and determining whether it is fit for a particular purpose and suitable for user’s method of application.

WARRANTY, LIMITED REMEDY, DISCLAIMER AND LIMITATION OF LIABILITY

Pro Form Products Ltd. (“Pro Form”) makes no warranty, either express or implied, and specifically excludes any implied warranties or conditions of quality, whether of merchantability, fitness or otherwise. On any claim, irrespective of the legal theory invoked, Pro Form’s total liability shall not exceed the purchase price of the product. At its option, Pro Form may instead replace or repair the product. In no event shall Pro Form be liable for any damages of any type, or for loss. The technical information, recommendations and other statements contained in this document are based upon tests or experience that Pro Form believes are reliable, but the accuracy or completeness of such information is not guaranteed.