

Aircraft Paint Stripper PF 747, PF 748

Aircraft Paint Stripper is a new and improved formulation for the removal of aftermarket paint and coatings. It will remove acrylics, epoxies, enamels, lacquers, polyurethanes and most other automotive finishes. Starts working in less than 15 mintues and clings well to vertical surfaces. It will lift multiple layers and is water rinseable. **DO NOT USE ON AIRCRAFT.**

P R O D U C T	SIZE
PF 748	946 ml (U.S. Quart)
PF 747	3.78 L (U.S. Gallon)

READ ALL INSTRUCTIONS AND SAFETY PROCEDURES PRIOR TO USING!

IMPORTANT! This product contains hazardous materials.

Proper protective equipment should be used at all times. Please consult labels on each product as well as the safety data sheet for complete safe handling procedures and personal protection information.

NOTE: TEST ON A HIDDEN AREA BEFORE USING TO MAKE SURE THE PRODUCT PERFORMS TO YOUR SATISFACTION.

REMOVES:

- Acrylics
- Epoxies
- Enamels
- Lacquers
- Polyurethanes
- Other automotive finishes

ADVANTAGES

- Powerful strength
- Fast acting
- Easy application
- Easy removal

SURFACE PREPARATION:

Clean with PF 605 Wax and Grease Remover (Strong). For faster penetration of the paint stripper, sand the surface with an 80 grit before applying the product.

DIRECTIONS FOR USE:

- 1. Use in a well ventilated area.
- 2. Open container slowly to relieve pressure thay may build up.
- 3. Apply PF 747or PF 748 Brush in one stroke and one direction only. Do not rebrush as increased brushing will cause solvent evaporation and reduce effectiveness.
- 4. Allow stripper to penetrate the finish
 - a) Acrylic Lacquer will soften in 10 to 15 minutes.
 - b) Other finishes will blister in 20 to 30 minutes.
- 5. When action is completed, scrape off with a flexible putty knife or squeegee.



Aircraft Paint Stripper PF 747, PF 748

- 6. Rinse thoroughly with either:
 - a) Water from a hose
 - b) Water dipped rags or steel wool; or
 - c) Solvent dipped rags. (Use lacquer thinner or paint thinner).
- 7. Clean surface with PF 603 Wax and Grease Remover (Mild).
- 8. Dry thoroughly prior to applying new finish.

USE WITH EXTREME CAUTION ON FIBERGLASS, PLASTICS, OR ANY OTHER SYNTHETIC SURFACE.

Rinse with water immediately after blistering of the coating to be removed. Work small area at a time.

For best results, apply at temperatures between 65°F and 90°F (18°C and 32°C), and avoid direct sunlight and strong breezes.

Use proper precautionary measures for handling and follow all proper disposal procedures and regulations.

USE CAUTION WHEN OPENING IF STORED ABOVE 26°C (80°F).

TECHNICAL DATA:

	PF 748, PF 747
Physical State	Liquid
Color:	Cloudy, Pale yellow
Odour:	Strong odour
Solubility:	Partially in water
Flash point:	Not to Boiling (Closed Cup)
Auto ignition temperature:	Not available
VOC	650.3 g/L • 5.43 lbs/gal

PRECAUTIONARY INFORMATION

Refer to product label and Safety Data Sheet for health and safety information before using this product.

SAFETY CONSIDERATION

Safety Data Sheets are available at www.proformproducts.com or upon request at info@proformproducts.com. These are provided to help our customers satisfy their own handling, safety and disposal needs, and those required by local applicable health and safety regulations. Our Safety data sheets are updated regularly, therefore, please review the most current Safety Data Sheet before handling or using any product.

TECHNICAL INFORMATION

The technical information, recommendations and other statements contained in this document are based upon tests or experience that Pro Form believes are reliable, but the accuracy or completeness of such information is not guaranteed.

PRODUCT USE

Many factors beyond Pro Form's control and uniquely within user's knowledge and control can affect the use and performance of a Pro Form product in a particular application. Given the variety of factors that can affect the use and performance of a Pro Form product, user is solely responsible for evaluating the Pro Form product and determining whether it is fit for a particular purpose and suitable for user's method of application.



Aircraft Paint Stripper PF 747, PF 748

WARRANTY, LIMITED REMEDY, DISCLAIMER AND LIMITATION OF LIABILITY

Pro Form Products Ltd. ("Pro Form") makes no warranty, either express or implied, and specifically excludes any implied warranties or conditions of quality, whether of merchantability, fitness or otherwise. On any claim, irrespective of the legal theory invoked, Pro Form's total liability shall not exceed the purchase price of the product. At its option, Pro Form may instead replace or repair the product. In no event shall Pro Form be liable for any damages of any type, or for loss. The technical information, recommendations and other statements contained in this document are based upon tests or experience that Pro Form believes are reliable, but the accuracy or completeness of such information is not guaranteed.