

Premium quality, fast drying enamel paint. It offers excellent adhesion to metal, wood, fibreglass, and rigid parts.

PRODUCT	SIZE	COLOR
PF 518	340 g (12 oz) Aerosol	Flat Black
PF 519	340 g (12 oz) Aerosol	Gloss Black
PF 524	283 g (10 oz) Aerosol	Semi Gloss Black

READ ALL INSTRUCTIONS AND SAFETY PROCEDURES PRIOR TO USING!

IMPORTANT! This product contains hazardous materials.

Proper protective equipment should be used at all times. Please consult labels on each product as well as the safety data sheet for complete safe handling procedures and personal protection information.

NOTE: TEST ON A HIDDEN AREA BEFORE USING TO MAKE SURE THE PRODUCT PERFORMS TO YOUR SATISFACTION.

SUITABLE SUBSTRATES:

- Metal
- Wood
- Fibreglass
- Rigid plastics

ADVANTAGES:

- Fast drying
- Excellent adhesion

DIRECTIONS FOR USE:

For best results, use only when temperature of material and surfaces are between 21°C and 24°C (70°F and 75°F).

1. Remove rust, wash with soap and water. Clean metal surfaces with PF 605 Wax and Grease Remover (Strong), plastic surfaces with PF 606 Plastic Parts Cleaner. Wipe dry while the surface is still wet. Bare metal should be primed with PF 654 Self Etching Primer.
2. Shake can for 1 minute after mixing ball moves freely. **NOTE:** Insufficient mixing may cause permanent plugging of the sprayhead.
3. Hold can 20-25 cm (8-10") from surface. Move can back and forth, releasing spray head after each stroke. Overlap each stroke. Two thin coats are recommended rather than one heavy coat. Allow 5 minutes flash time between coats.
4. When finished, turn can upside down and spray 3 seconds to clean sprayhead.

DRY TIMES:

	PF 519, PF 518, PF 524
Touch:	15 minutes
Tack Free:	10 to 15 minutes
Handle:	1 hr
Recoat:	30-45 minutes or wait 24 hours until coating is fully cured
Sand:	1 -2 hour

CAUTION: It is important to test the compatibility of this product with your paint system.

INCLUDES 2 SPRAYHEADS:

- Black sprayhead provides a 6½ width fan spray.
- White sprayhead provides a 2½ width fan spray.

**TECHNICAL DATA:**

	PF 518	PF 519	PF 524
Physical State	Aerosol	Aerosol	Aerosol
Color:	Black	Black	Black
Odour:	Hydrocarbon odour	Characteristic odour, strong solvent	Hydrocarbon odour
Solubility :	Not soluble in water	Not soluble in water	Not soluble in water
Flash point:	-4°C (25°F)	-18°C (0°F)	-11°C (12°F)
Auto ignition temperature:	460°C (860°F) (propellant)	460°C (860°F) (propellant)	460°C (860°F) (propellant)

PRECAUTIONARY INFORMATION

Refer to product label and Safety Data Sheet for health and safety information before using this product.

SAFETY CONSIDERATION

Safety Data Sheets are available at www.proformproducts.com or upon request at info@proformproducts.com. These are provided to help our customers satisfy their own handling, safety and disposal needs, and those required by local applicable health and safety regulations. Our Safety data sheets are updated regularly, therefore, please review the most current Safety Data Sheet before handling or using any product.

TECHNICAL INFORMATION

The technical information, recommendations and other statements contained in this document are based upon tests or experience that Pro Form believes are reliable, but the accuracy or completeness of such information is not guaranteed.

PRODUCT USE

Many factors beyond Pro Form's control and uniquely within user's knowledge and control can affect the use and performance of a Pro Form product in a particular application. Given the variety of factors that can affect the use and performance of a Pro Form product, user is solely responsible for evaluating the Pro Form product and determining whether it is fit for a particular purpose and suitable for user's method of application.

WARRANTY, LIMITED REMEDY, DISCLAIMER AND LIMITATION OF LIABILITY

Pro Form Products Ltd. ("Pro Form") makes no warranty, either express or implied, and specifically excludes any implied warranties or conditions of quality, whether of merchantability, fitness or otherwise. On any claim, irrespective of the legal theory invoked, Pro Form's total liability shall not exceed the purchase price of the product. At its option, Pro Form may instead replace or repair the product. In no event shall Pro Form be liable for any damages of any type, or for loss. The technical information, recommendations and other statements contained in this document are based upon tests or experience that Pro Form believes are reliable, but the accuracy or completeness of such information is not guaranteed.